


# DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN	AMARETTINI 344
Lightfastness:	5	54004	 <p>Color: Amarettini 344 Collection: Rodeo Thickness: 1,4 - 1,6 mm</p>
Abrasion values:	<b>Level:</b>		
Dry	4 - 5	53339	
Wet	3 - 4		
Perspiration	3 - 4		
Permanent folding behavior: 20.000 bucklings	passed	53340	
Tensile strength: 20 N/mm	passed	53329	
SG-Test:	passed		
Burning behavior: EN1021 part I u. II	passed		
Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at: <a href="http://www.vegetable-tanned-leather.com/data-and-facts.html">www.vegetable-tanned-leather.com/data-and-facts.html</a>			
<b>Tested for</b> Heavy metals, chrome (Conducted by the German Institute of Environment in Bremen, 2014/2015)			

# DATA SHEET



## Results of the examination for chrome

Parameter	K 2300 FL-1 Ecopell 344 Amarettini KW 14 (mg/kg)	BG (mg/kg)	Requirements GOTs* (mg/kg)
chrome	<1	1	<1

\* Global Organic Textile Standard, Version 4.0, requirements for ingredients and accessories

## Results of the examination for heavy metals

Heavy metals	H 9379 FL-3 Ecopell 344 Amarettini KW 32 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)	Requirements ECARF (mg/kg)
Antimony	<0,5	0,5	1	-
Aluminium	70	10	500	-
Arsenic	<0,5	0,5	1	-
Lead	<0,5	0,5	1	-
Cadmium	<0,2	0,2	0,2	-
Chrome	17	1	50	40
Cobalt	<1	1	5	-
Mercury	<0,1	0,1	0,2	-
Nickel	<1	1	5	-
Titanium	<10	10	500	-
Zirconium	<5	5	500	-

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected