


DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN	BLACK RUSSIAN 430
Lightfastness:	4	54004	 <p>Color: Black Russian 430 Collection: Glamour Thickness: 1,4 - 1,6 mm</p>
Abrasion values:	Level:		
Dry	4 - 5	53339	
Wet	4 - 5		
Perspiration	4 - 5		
Permanent folding behavior: 20.000 bucklings	passed	53340	
Tensile strength: 20 N/mm	passed	53329	
Burning behavior: EN1021 part I u. II	passed		

Detailed information about light fastness, abrasion values, skin tolerance and burning behaviour can be found at:
www.vegetable-tanned-leather.com/data-and-facts.html

Tested for
Heavy metals, formaldehyde
(Conducted by the German Institute of Environment in Bremen, 2014)

DATA SHEET



Results of the examination for formaldehyde

Parameter	H 9119 FL-1 Ecopell 430 Black Russian KW 45 (mg/kg)	NG (mg/kg)	Anforderungen IVN Leder (mg/kg)	Anforderungen ECARF (mg/kg)
Methanal (formaldehyde)	4	3	50	50

Results of the examination for heavy metals

Heavy metals	H 9119 FL-1 Ecopell 430 Black Russian KW 45 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)	Requirements ECARF (mg/kg)
Antimony	<0,5	0,5	1	-
Aluminium	480	10	500	-
Arsenic	<0,5	0,5	1	-
Lead	<0,5	0,5	1	-
Cadmium	<0,2	0,2	0,2	-
Chrome	25	1	50	40
Cobalt	<1	1	1	-
Mercury	<0,1	0,1	0,2	-
Nickel	<1	1	5	-
Titanium	<10	10	500	-
Zirconium	<5	5	500	-

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected