

# DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
Lightfastness:	2 - 3	54004
Abrasion values:	<b>Level:</b>	
Dry	5	53339
Wet	5	
Perspiration	4 - 5	
Permanent folding behavior: 20.000 bucklings	passed	53340
Tensile strength: 20 N/mm	passed	53329
Burning behavior: EN1021 part I u. II	passed	

## WOMBAT 182



Color: Wombat 182  
Collection: Rodeo SOFT  
Thickness: 1,4 - 1,6 mm



Detailed information about light fastness, abrasion values, skin tolerance and burning behaviour can be found at:  
[www.vegetable-tanned-leather.com/data-and-facts.html](http://www.vegetable-tanned-leather.com/data-and-facts.html)

Tested for  
Heavy metals  
(Conducted by the German Institute of Environment in Bremen, 2015)

# DATA SHEET



## Results of the examination for heavy metals

Heavy metals	K 2263 FL I-5 Ecopell 182 Wombat KW 40 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)	Requirements ECARF (mg/kg)
Antimony	0,5	0,5	1	-
Aluminium	50	10	500	-
Arsenic	<0,5	0,5	1	-
Lead	<0,5	0,5	1	-
Cadmium	<0,2	0,2	0,2	-
Chrome	7	1	50	40
Cobalt	<1	1	5	-
Mercury	<0,1	0,1	0,2	-
Nickel	1	1	5	-
Titanium	<10	10	500	-
Zirconium	<5	5	500	-

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected